

# CLEARCLAD HSR E-COAT 「吉利凯」 HSR聚氨酯阴极电泳漆



**Clearclad HSR contains UV light stabilizer which protects dyes and other colourants for decoration of spectacle frames according to the demands of fashion. Following are the principle performance capabilities. Overall the Clearclad HSR process delivers a coating package particularly suited to the requirements of the spectacle frame coatings.**

「吉利凯」HSR电泳漆含有抗紫外光稳定剂，因此能防止其中所含色素的褪色。由于其特有之防人工汗性能，已成为世界独一无二为各大名牌眼镜制造厂商采用的电泳漆，其优越性能可通过下列测试。

**Pencil hardness (ASTM D3363):**

铅笔硬度 (ASTM D3363):

**Abrasion resistance (ASTM D968):**

摩擦抗性 (ASTM D968):

**Perspiration resistance (ANSI / BHMA):**

人工汗抗性 (ANSI / BHMA):

**Corrosion protection (ASTM B117):**

防腐性 (ASTM B117):

**UV light resistance (quv test):**

紫外光抗性 (QUV):

**Acetone rub test:**

丙酮摩擦次数:

**Pass4H (gouge method)**

通过4H

**Coefficient = 18 litres/mil**

系数 = 18 litres/mil

**Pass4 cycles**

通过四个循环测试

**(chromated brass) > 500hours**

with less than 2mm creep

经钝化铜片测试 > 500小时，蔓延扩散少于2微米  
("brass" colour dye) < DE2.0

(CIELAB) at 500 hours

CIELAB 通过 500小时测试

**> 1000double rubs**

> 1000来回摩擦



**HAWKING INTERNATIONAL FAR EAST GROUP**

**浩金国际远东集团**



HAWKING INTERNATIONAL (HK) LTD

浩金国际(香港)有限公司

Tel: (852) 2796-8963

Fax: (852) 2796-8149

E-mail: hwkfgrp@pacific.net.hk

Website: www.hawking.com.hk

TAIWAN HAWKING INTERNATIONAL LTD.

台湾浩金国际有限公司

Tel: (886) 02-29710698

Fax: (886) 02-29717024

E-mail: hawking@ms65.hinet.net

HAWKING FINE CHEMICALS (BEIJING) CO. LTD.

浩金精细化工(北京)有限公司

Tel: (86) 010-61566018/010-61566028

Fax: (86) 010-69573838

E-mail: beijing@hawking.com.cn

HAWKING FINE CHEMICALS (SHANGHAI) CO. LTD.

浩金精细化工(上海)有限公司

Tel: (86) 021-57448275

(86) 021-57448276

Fax: (86) 021-57442609

E-mail: shanghai@hawkingsh.com

HAWKING INTERNATIONAL (HK) LTD.

HUMEN REPRESENTATIVE OFFICE

浩金国际(香港)有限公司东莞虎门代表处

Tel: (86) 0769-85268018/0769-85268019

Fax: (86) 0769-85268020

E-mail: hm01@hawking-grp.com